



Technical Data Sheet

Stabiphane PPC TS

Both sides matt PPC polyester film

Base(s) Clear bases

Technical data

Properties	Method	Unit	36µm
General			
Total thickness	Internal	µm	50
Relative density (23°)	ASTM D.1505	g/cm ³	1.395
Melting point	-	°C	260
Mechanical			
Tensile strength at break	ASTM D.882	daN/mm ²	21
Elongation at break	ASTM D.882	%	150
Thermal			
Shrinkage MD 150°C-30mn	ASTM D.1204	%	<1.0
Shrinkage TD 150°C-30mn	ASTM D.1204	%	<0.6
Specific			
Smoothness	TAPPI T.479	sec.	80
Opacity UV	Internal	%	60
Surface resistivity	ASTM D.257	Ω.cm	10 ¹¹
Whiteness	Internal	%	>79

MD: Machine direction

TD: Transversal direction

All typical values of properties relate to assessment made at time of manufacture.
This specification is confidential and submitted to the other party for mutual agreement.

v3.0 created: 01/05/2002 modified: 30/01/2012