



Technical Data Sheet

Arcophane WO TCA 08 2F

TCA treated both sides white opaque polyester film

Base(s)	White bases
----------------	-------------

Technical data

Properties	Method	Unit	36µm
General			
Total thickness	Internal	µm	36
Relative density (23°)	ASTM D.1505	g/cm ³	1.395
Melting point	-	°C	260
Mechanical			
Tensile strength at break	ASTM D.882	daN/mm ²	15
Elongation at break	ASTM D.882	%	115
Thermal			
Shrinkage MD 150°C-30mn	ASTM D.1204	%	<1.0
Shrinkage TD 150°C-30mn	ASTM D.1204	%	<0.8
Specific			
Surface tension	ASTM D.2578	dynes/cm	70
Opacity	ASTM D.1003	%	N.A.

MD: Machine direction
 TD: Transversal direction

All typical values of properties relate to assessment made at time of manufacture.
 This specification is confidential and submitted to the other party for mutual agreement.

v3.0 created: 01/05/2002 modified: 30/01/2012